



Be Professional, Be Supercolor!

Shanghai Supercolor Chemical Technology Co., Ltd was incorporated by specialists who have long term working experience in pigment and pigment-relative industries.

Shanghai Supercolor Chemical Technology Co., Ltd is responsible for selecting qualified pigment from leading pigment manufacturers who are reliable and trustworthy to supply quality pigment in consistence for long time.

Our long time working experience, abundant pigment knowledge and qualified facilities for various application test guarantee that Supercolor could source those top-quality level pigment locally in China and QC every batch based on customers' specific method before delivery to save customers' QC job.

What we offer is not only products, but also technical advice and after-sale-service for customers.

Suplasto series pigment---wide range of commonly used pigment for plastic industry.

The benefits to use Suplasto Series pigment

- Batch to batch consistency of color hue and color strength
- Concentrated pigment particle size distribution
- Improved dispersibility
- Outstanding thermostability
- Excellent properties of light fastness and weather fastness
- Specific and continuous after-sale-service

Distributed by:



www.vanhornmetz.com

[Request Quote or Samples](#)

Supplier:

Address:

Postal Code:

Phone:

Fax:

E-mail:

Van Horn, Metz & Company, Inc.

201 East Elm Street, Conshohocken, PA

19428 USA

+1 (610) 828-4500

+1 (610) 828-0936'

info@vanhornmetz.com



Pigment Name	Full Shade (0.2% Pigment)	Reduction Shade (0.1%Pigment + 1% TiO ₂)	Fastness Property		
			Heat Resistance(°C)	Light Fastness	Migration
Suplasto Yellow SC-GR02 (C.I.Pigment Yellow 13)			200	6-7	4-5
Suplasto Yellow SC-WSR (C.I.Pigment Yellow 62)			230	6-7	3-4
Suplasto Yellow SC-HR02 (C.I.Pigment Yellow 83)			200	6-7	4-5
Suplasto Yellow SC-3RN (C.I.Pigment Yellow 110)			280	7-8	5
Suplasto Yellow SC-H961 (C.I.Pigment Yellow 138)			250	7-8	4-5
Suplasto Yellow SC-H2R (C.I.Pigment Yellow 139)			240	7	5



Pigment Specialist

上海秀乐化工科技有限公司

Shanghai supercolor chemical technology co., Ltd

Add: Bldg.5, No. 1500 Xinfei., Songjiang Industrial Zone, Shanghai, China 201611

Tel:+86-21-61023838*8001, 67601408

Fax:+86-21-51026050, 67600928

URL:www.supercolor.cn

Pigment Name	Full Shade (0.2% Pigment)	Reduction Shade (0.1% Pigment + 1% TiO ₂)	Fastness Property		
			Heat Resistance(°C)	Light Fastness	Migration
Suplasto Yellow SC-3GP (C.I.Pigment Yellow 155)			240	7-8	3-4
Suplasto Yellow SC-WGP (C.I.Pigment Yellow 168)			230	6-7	4-5
Suplasto Yellow SC-HG (C.I.Pigment Yellow 180)			280	6-7	4-5
Suplasto Yellow SC-KP (C.I.Pigment Yellow 183)			270	7-8	4-5
Suplasto Yellow SC-HGR (C.I.Pigment Yellow 191)			280	6-7	4-5
Supigmento Orange SC-RL (C.I.Pigment Orange 34)			200	5	4-5



Pigment Name	Full Shade (0.2% Pigment)	Reduction Shade (0.1% Pigment + 1% TiO ₂)	Fastness Property		
			Heat Resistance(°C)	Light Fastness	Migration
Supigmento Orange SC-GP (C.I.Pigment Orange 64)			280	7-8	5
Supigmento Orange SC-RA (C.I.Pigment Orange 73)			280	7-8	5
Suplasto Red SC-2BP (C.I.Pigment Red 48:2)			220	6-7	4-5
Suplasto Red SC-2BSP (C.I.Pigment Red 48:3)			230	5-6	4-5
Suplasto Red SC-CN (C.I.Pigment Red 53:1)			270	2-3	4-5
Suplasto Red SC-4BP (C.I.Pigment Red 57:1)			230	6-7	4-5



Pigment Name	Full Shade (0.2% Pigment)	Reduction Shade (0.1% Pigment + 1% TiO ₂)	Fastness Property		
			Heat Resistance(°C)	Light Fastness	Migration
Suplasto Red SC-ED (C.I.Pigment Red 122)			280	7-8	5
Suplasto Red SC-BRN (C.I.Pigment Red 144)			270	7-8	5
Suplasto Red SC-RN (C.I.Pigment Red 166)			270	7-8	5
Suplasto Red SC-F3RK (C.I.Pigment Red 170)			240	6-7	4
Suplasto Red SC-F5RK (C.I.Pigment Red 170)			240	6-7	4-5
Suplasto Red SC-A3B (C.I.Pigment Red 177)			250	7	4-5



Pigment Name	Full Shade (0.2% Pigment)	Reduction Shade (0.1% Pigment + 1% TiO ₂)	Fastness Property		
			Heat Resistance(°C)	Light Fastness	Migration
Suplasto Red SC-30 (C.I.Pigment Red 254)			280	7-8	5
Supigmento Violet SC-RP (C.I.Pigment Violet 19)			300	7-8	5
Suplasto Violet SC-RLP (C.I.Pigment Violet 23)			250	7-8	4-5
Suplasto Blue SC-BS512 (C.I.Pigment Blue 15:1)			300	7-8	5
Suplasto Blue SC-BGSP (C.I.Pigment Blue 15:3)			300	7-8	5
Suplasto Green SC-GP (C.I.Pigment Green 7)			280	7-8	5